

BNL-228249-2025-TECH EIC-ADD-TN-122

Electrical resistivity testing from 300K to 20K of some commercially available copper, aluminum and nickel

F. Micolon

May 2025

Electron-Ion Collider

Brookhaven National Laboratory

U.S. Department of Energy

USDOE Office of Science (SC), Nuclear Physics (NP)

Notice: This technical note has been authored by employees of Brookhaven Science Associates, LLC under Contract No.DE-SC0012704 with the U.S. Department of Energy. The publisher by accepting the technical note for publication acknowledges that the United States Government retains a non-exclusive, paid-up, irrevocable, worldwide license to publish or reproduce the published form of this technical note, or allow others to do so, for United States Government purposes.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or any third party's use or the results of such use of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof or its contractors or subcontractors. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Electrical resistivity testing from 300K to 20K of some commercially available copper, aluminum and nickel

F.Micolon, S. Nayak, B. Golden

Revision	Date	Main modification
1.0	5/29/2025	Initial release

1. Introduction

Through 2024-2025 some alloys of copper, aluminum and nickel were tested in a cryogenic electrical resistivity measurement bench, with the primary intent to help inform the design of superconducting current leads for EIC [1]. The measurement spans temperature from 293 K to around 20 K. The material tested are:

- a) Brass 260 (UNS C26000)
- b) Copper OFHC 101-O (UNS C10100)
- c) Copper ETP 110-O (C11000)
- d) copper ETP 110-H02 (C11000)
- e) Copper ETP 110-H04 (UNS C11000)
- f) Copper DHP 122-H02 (UNS C12200)
- g) Aluminum 1100-O (UNS A91100)
- h) Aluminum 2024-T4 (UNS A92024)
- i) Nickel 200 (UNS N02200)

This report aims to detail the results and discuss by comparing them with literature data. A table of the measured resistivity values is available in appendix 2 for future use.

2. Test bench description

The test bench used is described in Ref. [2].

The sample is cooled by a cryocooler and the electrical excitation of the samples is AC with a 5 Hz excitation frequency to filter out noise and thermoelectric effects. This means that highly conductive alloys at very low temperatures may be affected by skin depth effect. This effect is proportional to the square root of electrical conductivity. For this work the samples geometry of highly conductive alloys was adequate, and we made sure no skin depth effect was significant (material cross section <0.5x skin depth for all temperature).

The voltage is measured in a 4 wire arrangement and the current is set with precision by the power supply.

3. Samples geometry

Two geometries of samples were used, a flat ribbon and bent tubular samples. Flat ribbon follow the drawing EIC-HSR-SCN-0112 available in annex 1.

Material	Sample thickness
Brass 260	0.032" (0.8 mm)
Cu ETP 110-0	0.01" (0.254 mm)
Al 1100-0	0.01"(0.508 mm)
AI 2023 T3	0.02"(0.5 mm)

An adapter piece was later made to allow testing of square and tubular products.

Material	Sample dimensions
Cu ETP 110-H02	Square – width 0.09"
Cu ETP 110-H04	Rod OD Φ 0.125" (Φ 3.175 mm)
Cu DHP 122-H02	Tube OD Φ 0.125" / ID 0.097" (Φ 3.18/2.46 mm)
Nickel 200	Strip 0.25" wide – 0.018" thick
Cu ETP 110-H04 Cu DHP 122-H02 Nickel 200	Rod OD Φ 0.125" (Φ 3.175 mn Tube OD Φ 0.125" / ID 0.097" (Φ 3.18/ Strip 0.25" wide – 0.018" thic

Results and discussion





Figure 1 Brass 260 - Electrical resistivity 296 K to 20 K

The measured electrical resistivity of the brass 260 sample is lower than expected by about 13%. This is consistent along the temperature decrease. The brass from the literature data [3] is mentioned to be hardened to $\frac{3}{4}$ hard while the brass 260 sample we tested was given as $\frac{1}{2}$ hard. The lower strain hardening in our sample may explain the lower resistivity observed throughout.



b. Copper OFHC 101-O (UNS C10100)

Figure 2 Copper 101-O - Electrical resistivity 296 K to 29 K – Linear scale (top) Log-scale (bottom)

The RRR measured is **219** which is consistent with a high purity annealed copper.

A small mismatch between the measurement and literature data [4] is present at warm temperature only. The room temperature resistivity of 1.56E-8 ohm.m seems low while 1.70E-8 ohm.m is typical for pure copper at 295K.



c. Copper ETP 110-O (UNS C11000)



Figure 3 Copper 110-O - Electrical resistivity 296 K to 29 K – Linear scale (top) Log-scale (bottom)

The RRR measured is **273**. The match with literature data computed with a RRR273 [4] is excellent.



d. Copper ETP 110-H02 (UNS C11000)

Figure 4 Copper 110-H02 - Electrical resistivity 296 K to 29 K – Linear scale (top) Log-scale (bottom)

The RRR measured is **91**, a significant reduction from annealed copper (see section b. and c.). The match with literature data [4] is excellent. Although the actual hardness of this sample is unknown, it is specified as H02 which corresponds to about 20% of area reduction. Ref. [4] gives a estimate of RRR from cold work and the range for 20% cold work is around RRR 60-90 which is consistent with the results.

e. Copper ETP 110-H04 (UNS C11000)

Due to an acquisition issue, the cool-down resistivity data was not usable. However, the RRR measured is **61**. For a full hard H04 copper, the elongation is around 30%. The RRR obtained is consistent with the RRR predicted in [4] for the amount of cold work.

f. Copper DHP 122-H02 (UNS C12200)

Copper DHP has a relatively high level of impurity, in particular phosphorus, which is among the most effective impurity to reduce the electrical resistivity and RRR (Ref.[4] Fig 8.1). A RRR of **5.3** is measured.



Figure 5 Copper 122-H02 - Electrical resistivity 296 K to 29 K – Linear scale (top) Log-scale (bottom)



g. Aluminum 1100-O (UNS A91100)

Figure 6 Aluminum 1100-O - Electrical resistivity 296 K to 29 K – Linear scale (top) Log-scale (bottom)

A slight discrepancy is seen all along the curve, it is particularly notable on the log-curve that the discrepancy is a proportion of the total resistivity between 12% (at room temperature) and 20% (at 20K). The RRR is **24**.







The match with literature data is not good. This may be in part due to the different heat treatment of the alloy tested and the alloy in the literature.





The measurement lowest temperature is around 20.4 K where the RRR is **3.7**. The room temperature resistivity is consistent with literature. No literature was found for cryogenic resistivity.

4. Summary

A series of metals and alloys have been tested to measure their electrical resistivity at cryogenic temperature and assess their predictability using literature correlations. The observations made are summarized in the following table :

Material	Room temperature (293 K) resistivity measured (ohm.m)	RRR measured	Match with literature data
Brass 260	6.06E-8	1.65	Poor
Copper OFHC 101-O	1.56E-8	219	Good
Copper ETP 110-0	1.72e-8	273	Excellent
Copper ETP 110-H02	1.75E-8	91	Excellent
Copper ETP 110-H04	N/A	61	N/A
Copper DHP 122-H02	2.00E-8	5.3	Good
Aluminum 1100-0	2.92E-8	23.8	Good
Aluminum 2024-T3	5.52E-8	1.9	Poor
Nickel 200	9.64E-8	3.7	N/A

It is noted that copper are well described by literature correlations, especially for high purity copper. The correlations available for Aluminum was also satisfactory. No correlation has been found for Nickel 200. Alloys have shown significant dispersions from literature data.

5. Reference

[1] F.Micolon et al. "Design of a new 12x150A helium cooled current lead for EIC" Proc CEC-ICMC25, in publication

[2] S. Verdu-Andres "An apparatus to measure the residual resistivity ratio" BNL technical report BNL-226192-2024-TECH / EIC-ADD-TN-103

[3] A.F. Clark, G.E. Childs and G.H. Wallace, "Electrical resistivity of some engineering alloys at low temperatures" Cryogenics, v10, p295, August (1970)

[4] N. Simon, E. Drexler, and R. Reed, "Properties of copper and copper alloys at cryogenic temperatures. Final report," Office of Scientific and Technical Information (OSTI) doi:10.2172/534030

[5] Hust, J. and Lankford, A. (1984), Thermal conductivity of aluminum, copper, iron, and tungsten for temperatures from 1 K to the melting point:, , National Institute of Standards and Technology, https://doi.org/10.6028/NBS.IR.84-3007





Appendix 2 – Electrical resistivity measured summary table

Temperature	Brass 260	C101-0	C110-0	C110-H02	C122-H02	Al1100-0	Al2024-T3	Nickel 200
293	6.028E-08	1.552E-08	1.671E-08	1.743E-08	1.982E-08	2.878E-08	5.470E-08	9.654E-08
290	5.998E-08	1.532E-08	1.650E-08	1.722E-08	1.960E-08	2.840E-08	5.434E-08	9.489E-08
280	5.904E-08	1.471E-08	1.582E-08	1.652E-08	1.897E-08	2.722E-08	5.317E-08	9.041E-08
270	5.817E-08	1.410E-08	1.514E-08	1.583E-08	1.833E-08	2.603E-08	5.207E-08	8.626E-08
260	5.730E-08	1.348E-08	1.446E-08	1.513E-08	1.769E-08	2.482E-08	5.095E-08	8.238E-08
250	5.637E-08	1.285E-08	1.379E-08	1.444E-08	1.705E-08	2.367E-08	4.984E-08	7.930E-08
240	5.548E-08	1.225E-08	1.312E-08	1.375E-08	1.642E-08	2.243E-08	4.870E-08	7.511E-08
230	5.460E-08	1.163E-08	1.243E-08	1.306E-08	1.579E-08	2.123E-08	4.760E-08	7.158E-08
220	5.369E-08	1.101E-08	1.176E-08	1.238E-08	1.513E-08	2.008E-08	4.649E-08	6.830E-08
210	5.278E-08	1.038E-08	1.109E-08	1.167E-08	1.450E-08	1.887E-08	4.537E-08	6.503E-08
200	5.188E-08	9.751E-09	1.040E-08	1.097E-08	1.386E-08	1.769E-08	4.427E-08	6.191E-08
190	5.099E-08	9.124E-09	9.730E-09	1.029E-08	1.322E-08	1.651E-08	4.316E-08	5.893E-08
180	5.006E-08	8.467E-09	9.051E-09	9.587E-09	1.257E-08	1.534E-08	4.206E-08	5.604E-08
170	4.913E-08	7.851E-09	8.364E-09	8.895E-09	1.192E-08	1.414E-08	4.095E-08	5.319E-08
160	4.822E-08	7.217E-09	7.667E-09	8.171E-09	1.128E-08	1.294E-08	3.984E-08	5.041E-08
150	4.727E-08	6.549E-09	6.981E-09	7.456E-09	1.062E-08	1.174E-08	3.871E-08	4.772E-08
140	4.630E-08	5.922E-09	6.284E-09	6.738E-09	9.954E-09	1.054E-08	3.761E-08	4.509E-08
130	4.536E-08	5.274E-09	5.584E-09	6.004E-09	9.300E-09	9.389E-09	3.650E-08	4.257E-08
120	4.437E-08	4.617E-09	4.885E-09	5.274E-09	8.633E-09	8.211E-09	3.541E-08	4.016E-08
110	4.342E-08	3.956E-09	4.182E-09	4.542E-09	7.973E-09	7.062E-09	3.434E-08	3.779E-08
100	4.242E-08	3.308E-09	3.492E-09	3.839E-09	7.313E-09	5.965E-09	3.329E-08	3.563E-08
90	4.139E-08	2.638E-09	2.798E-09	3.126E-09	6.648E-09	4.917E-09	3.232E-08	3.354E-08
80	4.041E-08	2.051E-09	2.152E-09	2.448E-09	6.025E-09	3.990E-09	3.141E-08	3.170E-08
77	4.007E-08	1.869E-09	1.957E-09	2.233E-09	5.837E-09	3.709E-09	3.115E-08	3.117E-08
70	3.939E-08	1.472E-09	1.530E-09	1.786E-09	5.424E-09	3.125E-09	3.061E-08	3.004E-08
60	3.848E-08	9.374E-10	1.008E-09	1.221E-09	4.879E-09	2.457E-09	2.993E-08	2.889E-08
50	3.770E-08	5.341E-10	5.771E-10	7.624E-10	4.421E-09	1.904E-09	2.943E-08	2.766E-08
40	3.716E-08	2.816E-10	2.870E-10	4.465E-10	4.076E-09	1.541E-09	2.914E-08	2.699E-08
30	3.681E-08	1.324E-10	1.290E-10	2.669E-10	3.864E-09	1.330E-09		2.662E-08
20	3.673E-08	7.896E-11	7.185E-11	2.018E-10		1.240E-09		2.647E-08
15		7.188E-11	6.380E-11					

Appendix 3 – Sample material certificates

1. Brass 260 (UNS C26000)

No certificate were available. The vendor website mentions they are half-hard (H02) with elongation 27%. Cu content is 68.5-71.5% and zinc content 28.38-31.38%.

2. Copper OFHC 101-O (UNS C10100)

No material certificates were supplied with this sample.

3. Copper ETP 110-O (C11000)



United States Brass and Copper 1401 Brook Drive Downers Grove, IL 60515 USA

Bill to: Trinity Brand 280 Shore Drive Burr Ridge, IL 60527 USA		Ship to: Trinity Brand Indu 280 Shore Drive Burr Ridge, IL 605 USA	ustries 527
Sales order	20RSO62199	Packing slip	20RPS70007
Customer PO	19470 MRS	Shipment date	11/13/2023
ltem number	COL0141	Product description	110 COPPER Soft 0.010 x 12.0000 x Coil ASTM B152 DFARS/RoHS/REACH Compliant Melt & manufactured USA
Heat number	258349		
<u>Chemical analysis</u> Cu = 99.9600			
Mechanical analysis			
ASTM = B 152 / B152M mm Other = Melt/Mfg: USA Tensile = 34,100	-19 Conductivity = IACS 101.5% Elongation = Resistivity = Rockwell = Yield = 8,300	= 41.0% GrainSize = .025 Surface =	
Other			
Thickness =			

Product certification

I certify that the above figures are a true and correct copy of those contained in the records of this company.

Amy Peandro QUALITY MANAGEMENT

4. Copper ETP 110-H02 (C11000)

The sample was a conductor salvaged from one of the original RHIC 12x150 A current lead. No material certificates were available at the time of testing. It is mentioned to be half-hard (H02) per the original drawings.

5. Copper ETP 110-H04 (UNS C11000)

18Apr23 13:50	TEST	CERT	IFICATE	No:	BHM 671478
THREE D ME 5462 INNOV VALLEY CIT Tel: 330 22	TALS, INC. ATION DRIVE Y, OHIO 44280 20 0451 Fax: 330 220	0471	P/O No KA-26633 Rel S/O No BHM 3230 B/L No BHM 3130 Inv No	3400 075-001 083-002 Shp Inv	18Apr23
Sold To: MCMASTER CA PO BOX 5510 CHICAGO, II	(71416) ARR SUPPLY CO 6 L 60680		Ship To: (3 MCMASTER CARR 3 200 NEW CANTON ROBINSONVILLE,	3) SUPPLY CO WAY NJ 08691	
Tel: 630-60	00-2878 Fax: 630-993	-3085			
	CERTIFICATE of ANAL	YSIS and	TESTS	Cert. No: B	HM 671478 18Apr23
Part No 100549 COPPER ROD HARD .1250 Nom X 12	DRAWN ROUND ROD .0000"			Pcs 168	Wgt 8
Heat Number K74021110003	Tag No 333014 HRF=<89.60>/IAC ELONG=<12.20>/A	S=<101.50 STM= <b18< td=""><td>)>/BEND=<120:GO0 7-20></td><td>Pcs 168 DD>/TSksi=<5</td><td>Wgt 8 8.00></td></b18<>)>/BEND=<120:GO0 7-20>	Pcs 168 DD>/TSksi=<5	Wgt 8 8.00>
Heat Number K74021110003	*** Chemical A Cu=<99.99> PERU	nalysis '	***		
THIS IS TO CERT: AND/OR PHYSICAL CORRECT, AS CON OF THE COMPANY.	IFY THAT THE CHEMICA TEST RESULTS EXHIBI NTAINED WITHIN THE R	L ANALYS TED HERE ECORDS	IS IN ARE		
QUALITY MANAGER					
•					
John Bakuhn, Jr					

6. Copper DHP 122-O (UNS C12200)



CERTIFICATE OF COMPLIANCE WITH CHEMISTRY

CUSTOMER:	MCMAS	TER-CARR SUPPLY	DATE:	09/05/2023
CUSTOMER PO	<u>#:</u>	KA-68437380	LOT #:	0235804

This document certifies that the furnished product shipped against the above purchase order meets all requirements and instructions as needed. Unless otherwise noted, material conforms to the appropriate specification referenced below for composition and mechanical properties or to the standards set forth in the purchase order submitted by the customer.

PART NO:	M1856
DESCRIPTION:	122 COPPER TUBING, SEAMLESS, 1/2 HARD TEMPER, 1/8"±.002" OD x
	.014"±.001" WALL, IN 1FT LENGTH, ASTM B251
	***ELECTRONICALLY DELIVERED CHEM CERT
SSPECIFICATION:	
QUANTITY:	183 EACH
COMMENTS:	
	Reference # 11762: Heat: 164017, , P: .0369, Cu: 99.956

NOTE: Raw material sold is not warranted for any particular application and liability is strictly limited to replacement only.

Sincerely,

dogh. Authorized Signature

7. Aluminum 1100-O (UNS A91100)



CERTIFICATE OF ANALYSIS

Phone: (888) 539-5602 Phone: (440) 201-2235 Fax: (440) 201-2239 www.cometmetals.com 6225 Camp Industrial Rd, Solon, OH 44139

CUSTOMER #:	TRIIND	PRODUCT:	ALUMINUM	SHIPMENT :	04182022
PO # :	18676 MRS	CMI LOT # :	30.0A06 2636	SO #:	48674

BILL TO:	SHIP TO:
TRINITY BRAND INDUSTRIES	TRINITY BRAND INDUSTRIES
280 SHORE DRIVE	280 SHORE DRIVE
WILLOWBROOK, IL 60527	WILLOWBROOK, IL 60527

DESCRIPTION OF MATERIAL:	COMET PO #: 21-2636
ALUM 1100 ANN MF .020" +/0035"	
24.000" WIDE X COIL	
16" IDFC	
MAX 500 LBS / ROLL	
DOMESTIC MATERIALS PER ASTM B209	
DFARS/ROHS/REACH COMPLIANT	
MIN 3500 PSI & MIN, 20% FLONGATION MIN	

QUANTITY:	2,608 LBS
-----------	-----------

CHEMIC	AL COMPOS	ITION:			
Si + Fe	Cu	Mn	Zn	Other	AI
0.95	0.05 - 0.20	0.05	0.10	0.15	99.00
MAX		MAX	MAX	MAX	MIN

1	MECHANICAL COMP	POSITION:
ULTIMATE TENSILE	YIELD	ELONGATION%
14.39 KSI	6.44 KSI	32.14%
MILL/HEAT#		
1309189	1	

The undersigned certifies that the material, process and testing used in the fabrication of this order meets all applicable specifications required in the item description.

Authorized Signature:

Linda Selet.

Date: 4/18/2022

8. Aluminum 2024-T4 (UNS A92024)





https://Online.KaiserAluminum.com

Kaiser Aluminum Trentwood Works PO Box 15108 Spokane Valley WA 99215-5108 15000 E Euclid Spokane Valley, WA 99216 (509) 927-6317

CUSTOMER PO NUMBER:	w	ORK PACKAG	E: CUS	TOMER PAI	RT NU	IMBER	२ :	SHIP	RUN/LOAD:	GOV'T CO	NTRACT NUMBER:
5400648752-R05-10			ALF	LR01578-4	48			2006	659/9		
KAISER ORDER NUMBER:		SHIP DATE		ALLOY:	CLAD):	TEMPER:		PRODUCT DESC	CRIPTION:	
1374367-1		03/30/202	3	2024	BAR	E	тз		HT Flat Sheet		
WEIGHT SHIPPED:	QUANTITY:		TRUCK B/I	_ #:	GAUG	GE:			DIAMETER/WID	TH:	LENGTH:
3147 LB	219 PCS ES	ST.	20105111	1	0.02	.0200 IN 48.000 IN 144.000 IN			144.000 IN		
SHIP TO:						SOLD	TO:				
COPPER & BRASS SALES 5545 CHET WAGGONER COURT SOUTH BEND, IN 46628 US						COF ATT P.O SOL	PPER & 'N: ACC . Box 51 JTHFIE	BR/ OUI 116 LD,	ASS SALES NTS PAYAB MI 48086 US	LE	

MHU 2708897: LOT 475198B8: 59 pieces MHU 2719260: LOT 481389B5: 160 pieces

Certified Specifications

AMS 4037/RevR~AMS-QQ-A-250/4/RevB~ASTM B209/B209M/Rev21A~CMMP 019/RevD~CMMP 025/RevW

LOT: 475198B8 CAST: 356 DROP: 07 INGOT: 1

Melted in (ASTM E8/B (EN 200	USA (557) (2-1)													
Tensile: T	'emper	Dir/#2	ſests		Ult	imate	KSI (MPA)	Yield 1	KSI	(MPA) Elo:	ngation	o}o
	тз	LT / (02 (M	in:Max)	6	6.0 : 455 :	67.0 462)		44.3 : (305 :	44. 309	.8	15	.3 : 15.	8
(ASTM E1251)														
Chemistry:	SI	FE	CU	MN	MG	CR	ZN	Т	I V	V	ZR		OTHER	
Actual	0.08	0.16	4.5	0.57	1.4	0.01	0.09	0.0	2 0.03	1 (0.01	TOT	0.02	

9. Nickel 200 (UNS N02200)

	CERTIFIED MATH	FRIAL TEST F	FPORT	No		1 HAUL0797
Exact Mill Duplicate	HA OPDER NOATEN	IDATE		PAGE	05859	THIS IS TO CERTIFY THAT ALL REQUIRED SAMPLINGS INSPECTIO AND TESTS HAVE BEEN PERFORMED IN ACCORDANCE WITH T
Dupicate	100045072 6	10/01	/10	1	2	ORDER AND SPECIFICATION REQUIREMENTS. THE TEST REPOR REPRESENTS THE ACTUAL ATTRIBUTES OF THE MATERN
•	QUANTITY	INSPECTED BY				FURNISHED AND THE VALUES SHOWN ARE CORRECT AND TRU THE MATERIAL DESCRIBED BY THIS CERTIFICATE IS IN FU
	2976 LBS	HA/SN				COMPLIANCE WITH ALL ORDER AND INSPECTION REDUIREMENT WE HEREBY CERTIFY THAT THE BELOW FIGURES ARE
and the second se	7 20117		1 8 9 C 9 C 9	0000		ACCORDANCE WITH THE SPECIFIED CONTRACT REDUIREMENTS
Exact Mill Duplicate	DESCRIPTIONNICKEL 200	AIN CR S	EET CR	ANN		Pert of
•	SHIPPED .0180 IN	36.0000	N 96.0	00 IN	CUT	
EN 10 204/DIN	50049 (TYPE 3.1)			WE CERT		
HEATS C MN	CHEN S	ICAL ANALYS	IS (WT.	X) NT		
· · · · · · · · · · · · · · · · · · ·						
N39U8AC 0.07 0.15	0.15 0.001	0.08	0.03	99.5		
OUNTRY OF ORIGIN, MELTED AND MA Welt Method, Aim + electrosi	NUFACTURED IN THE	USA				
	NECHAN	ICAL PROPER	TIES			
	HARD GRAIN YIEL	D TENSILE	XELC	R/A	DEC	
	NESS SILE . ZXPS	V IAA	5	x		
EAT/LOT - QUANTITY	X 100					
EAT/LOT - QUANTITY N39UBAG SP26N 150 PCS	. X 100		•			
EAT/LOT - QUANTITY N39UBAG SP26N 150 PCS ION TENP-KR15T - AS SHIPPED	. X 100 76.9 0348	0697	39.8			
EAT/LOT - QUANTITY N39UBAG SP26N 150 PCS JON TENP-HR15T -AS SHIPPED	X 100 76.9 0348	0697	39.8			