

A HOLLOW METAL O-RING AS A VACUUM SEAL FOR THE AGS

J. C. Schuchman

October 1965

Collider Accelerator Department
Brookhaven National Laboratory

U.S. Department of Energy

USDOE Office of Science (SC)

Notice: This technical note has been authored by employees of Brookhaven Science Associates, LLC under Contract No. AT-30-2-GEN-16 with the U.S. Department of Energy. The publisher by accepting the technical note for publication acknowledges that the United States Government retains a non-exclusive, paid-up, irrevocable, world-wide license to publish or reproduce the published form of this technical note, or allow others to do so, for United States Government purposes.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or any third party's use or the results of such use of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof or its contractors or subcontractors. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Accelerator Department
BROOKHAVEN NATIONAL LABORATORY
Associated Universities, Inc.

AGS DIVISION TECHNICAL NOTE

No. 6

J.C. Schuchman
October 11, 1965

A HOLLOW METAL O-RING AS A VACUUM SEAL FOR THE AGS

The hollow metal O-ring gasket shows good promise as a reliable direct replacement for the elastomer seals in the present AGS.

A comparison with the machined gaskets such as the "K" and "V" seals show that the metal O-ring is much less expensive, and more important, it can be shaped to fit any type flange or groove. In addition to circular gaskets it can replace the oval gasket on the split flange end of the AGS vacuum chamber. A machined gasket ("K" and "V") is only available in circular form.

The metal O-ring possesses the desired characteristics which are shown in previous work (see AADD-82); namely a resilient base metal plated with a softer metal. The plating flows into the surface irregularities and actually does the sealing while the ring material maintains the sealing force.

A problem associated with the metal O-ring is maintaining a uniform cross section at the welded butt joint. This section is frequently "necked down" and does not seal. An attempt is being made to resolve this by striking the entire ring between two parallel flat plates before plating. This procedure produces a slight flat on either side of the ring resulting in a ring of uniform height with parallel sealing surfaces.

Hollow metal O-rings of different cross sections are now being tested. If the initial tests are good a few metal O-rings will be installed in the AGS.

Distribution:

A. van Steenberg
J. Grisoli
C. Gould
V. Buchanan
D. Hooper
I. Polk