

BNL-104572-2014-TECH

AGS/AD/Tech Note No. 143;BNL-104572-2014-IR

LEAD PLATED C-RING EVALUATION

J. R. Jahelka

January 1978

Collider Accelerator Department Brookhaven National Laboratory

U.S. Department of Energy

USDOE Office of Science (SC)

Notice: This technical note has been authored by employees of Brookhaven Science Associates, LLC under Contract No.EY-76-C-02-0016 with the U.S. Department of Energy. The publisher by accepting the technical note for publication acknowledges that the United States Government retains a non-exclusive, paid-up, irrevocable, world-wide license to publish or reproduce the published form of this technical note, or allow others to do so, for United States Government purposes.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or any third party's use or the results of such use of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof or its contractors or subcontractors. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Accelerator Department BROOKHAVEN NATIONAL LABORATORY Associated Universities, Inc. Upton, New York 11973

AGS DIVISION TECHNICAL NOTE

<u>No. 143</u>

LEAD PLATED C-RING EVALUATION

J.R. Jahelka

January 27, 1978

Purpose

Υ.

To simulate the in ring use of a lead plated C-Ring to seal a vacuum joint when a moderate $(150^{\circ} - 200^{\circ}C)$ bakeout of a component and/or vacuum system is desired.

Test Setup

The lead plated C-Ring seals were retained in a standard C-Ring retainer and clamped between Marmon flanges by a standard AGS Ring Marmon clamp. Combinations of aluminum and stainless steel flanges were tested • in addition to a pair of aluminum flanges.

The interflange space was pumped by a CEC model 120 leak detector with a dectection sensitivity of 2 x 10^{-10} std c.c./sec. for Helium.

The seal and flange assembly was heated with a Cal-rod element on one flange to simulate a joint between baked and unbaked vacuum components. A temperature of $200^{\circ}C$ (392°F) was used as an upper temperature limit for this test.

Test Procedure

The flange and seal assemblies were cycled through the following steps until either five cycles were completed or failure occurred:

-2-

- 1. Pump down to 5×10^{-3} torr and leak check.
- 2. Heat to 200°C while maintaining vacuum and leak check.
- 3. Cool to room temperature still maintaining vacuum and leak check.

4. Bleed up to atmosphere.

After it was verified that 200°C was a safe operating temperature, one seal and flange assembly was subjected to a continuous temperature increase to determine the failure temperature.

Results

Two groups of seals were tested. Group I consisted of 2 ea. Pressure Science Inc. 8.622/187/20 Lead Plated C-Rings. These represent our standard AGS main chamber Marmon seals but with lead plating substituted for the Indium coating normally applied. One seal survived the five cycles and the other leaked on the initial pump down. It was learned from Pressure Science Inc., that the failure was probably due to the annealing process of the Inconel base metal of the C-Ring required when Indium plating is to be applied. For lead plating a stiffer C-Ring section is required.

Group II consisted of 4 ea. 8.622/187/20 Pressure Science Inc. Lead Plated C-Rings. These were standard Pressure Science A-7078 C-Rings, heat treated in accordance with the requirements for lead plating. One seal leaked on the initial pumpdown and the remaining three survived the five cycle test procedure. One of the surviving seals was heated until it failed. The temperature at failure was $270^{\circ}C$ ($518^{\circ}F$) which is well above the upper limit temperature used for testing. The seal that failed on initial pumpdown looked as though the lead plating was not uniform in thickness, an obvious seal defect that occurred during manufacture. Recommendations

Aluminum/Aluminum and Stainless Steel/Aluminum flange combinations were tested. Failures were attributed to defective seal manufacture. I concluded that a lead plated C-Ring will adequately seal a vacuum joint when a moderate bakeout is required; that is baking to 200[°]C can be accomplished while maintaining a vacuum tight joint. -3-

Detail Test Data

Group I

- Seal 1 8.622/187/20 Lead Plated C-Ring Manufacturer - Pressure Science Inc. Flanges - Aluminum/Aluminum Clamp bolt torque - 250 in. 1bs. Temperature - 200[°]C Number of cycles survived - 5
- Seal 2 8.622/187/20 Lead Plated C-Ring Manufacturere - Pressure Science Inc. Flanges - Aluminum/Stainless Steel Clamp bolt torque - 250 in. 1bs. Temperature -Number of cycles survived Leaked on initial pumpdown

Group II

Seal 1 8.622/187/20 Lead Plated C-Ring Manufacturer - Pressure Science Inc. Part number - A-7078 Flanges - Aluminum/Stainless Steel Clamp bolt torque - 250 in. 1bs. Temperature - 200°C Number of cycles survived - 3^{*} Seal 2 8.622/187/20 Lead Plated C-Ring Manufacturer - Pressure Science Inc. Part Number - A-7078

> Flanges - Aluminum/Stainless Steel Clamp bolt torque - 250 in. 1bs. Temperature - 200⁰C

Number of cycles survived - 5

[^] Heated to failure after 3 cycles - failure occurred at $270^{\circ}C$

-4-

Seal 3	3	8.622/187/20 Lead Plated (C-Ring	
		Manufacturer - Pressure Science Inc.		
		Part number - A-7078		
		Flanges - Aluminum/Ceramic	Coated Stainless Steel	
		Clamp bolt torque - 250 in. 1bs.		
		Temperature	Leaked on initial	
		Number of cycles survived	<pre>> pumpdown</pre>	
Seal 4	4	8.622/187/20 Lead Plated C-Ring		
		Manufacturer - Pressure Science Inc.		
		Part number - A-7078		
		Flanges - Aluminum/Aluminum	n	
		Clamp bolt torque - 250 in.	. 1bs.	
		Temperature - 200°C		
		Number of cycles survived -	- 5	

Distr: Dept. Admin. AGS Div. Designers AGS Div. ME's D. Davis R. Dryden MCR Log

ali e a con M

۰,

•